

## Ink Technologies

- **Aspect**  
Transparent, glossy finish
- **Applications**  
High viscosity varnish dedicated to relief printing
- **Major advantages**  
Great flexibility, good reactivity
- **Printing**  
Cylinder screen printing machines

UV INK



## TECHNICAL CHARACTERISTICS



**Rollers anilox**

Rollers anilox: DY, BY and BU



**Storage**

Two years in its original packaging stored in between + 5°C and + 35°C



**Dilution**

The UVRELR varnish is ready to use



**Drying**

UV RELR will polymerize under a UV dose of about 120 MJ/cm<sup>2</sup>



**Cleaning**

Cleaning with the solvent 77BIO, 77NETX2 or X3 is recommended



**Handling**

After extraction of the ink, open pots need to be carefully and promptly closed. Artificial or natural light can cause the start of polymerization and lead to the formation of a thin skin at the surface. For this reason, it is advisable to work in a low lighting or safelight environment



**Packaging**

UV RELR 1kg  
UV RELR 5 kg



**Hygiene and safety**

Although the products selected for the formulation are not dangerous as such, contact can cause allergic reactions in some particularly sensitive individuals. Ink soils on the skin should be cleaned as soon as possible with soapy water. In any case, refer directly to the safety sheets

### Guarantee reserves

Although the data indicated in this document have been established after thorough tests, they are only given as an indication. VFP Company cannot be held responsible in any way, it being understood that we recommend making tests before starting any production run. No salesman, representative or agent is entitled to provide a guarantee or any insurance which might contradict the above statement. Please always refer to our general sale conditions.